



# STANDARD PRILLED GYPSUM (CALCIUM SULFATE)

## Typical Analysis

Calcium (Ca).....23.28%  
 Sulfur (S).....18.62%  
 Calcium Sulfate (CaSO<sub>4</sub>).....79.00%  
 California:  
     Gypsum Equivalent...100.00%

Derived From: Mined Anhydrite Calcium Sulfate and Hydrated Calcium Sulfate.

## Grind Analysis Prior to Prilling

100% Passing 100 Mesh Sieve  
 90% Passing 140 Mesh Sieve  
 53% Passing 200 Mesh Sieve  
 25% Passing 325 Mesh Sieve

## Characteristics of Prilled Calcium Sulfate

Moisture Content.....<1%  
 Water Soluble Binder.....5%  
 Angle of Repose.....30°  
 SGN.....260  
 UI.....50  
 Bulk Density, Loose.....69 lbs./cu.ft.  
 Bulk Density, Tapped.....76 lbs. cu.ft.

Use in accordance with the recommendations of a qualified individual or institution, or according to an approved nutrient management plan.

Available in Bulk or 2000lb, 1000lb and 50lb bags.